




MOSAIC FILM (500 MICRON)




Silver
M01




Gold
M02




Black
M10



Dark Grey
M11



Brown
M13



S/Silver
M14

MOSAIC FILM

DESCRIPTION

Material for laser cutting applications

SPECIFICATION

Size: 27 cm x 45 m

N.W: 8 kg / roll

TRANSFER CONDITION

The following instructions are given as guideline only.

Temperature: 160°C (320°F)

Backside Press: 185°C (365°F)

Pressing time: 12 seconds

SUITABLE FOR

Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.

Not suitable for treated and dyed garments.

NOTICE

We offer you to test the product against the color migration.

Pressing instruction may change, according to the fabric type.

ÜRÜN TANIMI

Lazer ile kesim uygulamaları için malzeme

ÖZELLİKLER

Ebat: 27 cm x 45 m

Net Kilo: 8 kg / roll

BASIM TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlara göre.

Derece: 160°C (320°F)

Tersten Pres: 185°C (365°F)

Baskı süresi: 12 saniye

UYGUN KUMAŞLAR

Pamuk, polyester / pamuk karışımı, polyester / akrilik vb tekstiller için uygundur.

Boyanmış ve işlem görmüş kumaşlar için uygun değildir.

UYARI

Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.



Cut the image in reverse
Deseni tersten kesiniz



160°C (320°F) - 185°C (356°F)
160°C (320°F) - 185°C (356°F)




4 Bar pressure
4 Bar basınç



12 sec. for pressing
12 saniye



COOL Peel
Soğuk çekim



45°



After 24H with Application
Uygulamadan 24 saat sonra