



PU FLEX (90 MICRON)

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
1110046 Centarbel
Tested for harmful substances.
www.oeko-tex.com/standard100



S100
White


OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
1110046 Centarbel
Tested for harmful substances.
www.oeko-tex.com/standard100




S199
Black



S103
Ardesia



S105
Grey




S106
Ice Grey



S205
Navy Blue




S207
Middle Blue




S210
Blue 55




S230
Royal Blue




S240
Blue 48




S245
Teal Blue



S250
Torquoise




S255
Aqua Green




S260
Sapphire



S270
Blue Layette



S280
Sky Blue



S285
Lilic



S290
Purple



S300
Aubergine



S305
Violetto 16




S310
Brown




S320
Leather Brown




S330
Bordeaux



S333
Camel



S340
Cardinal Red




S350
Red




S360
Flame Red




S370
Orange




S375
Salmon




S380
Magenta




S390
Pink




S395
Rosa 14




S400
Violetto 17




S410
Gold Yellow



S430
Medium Yellow




S440
Lime




S450
Lemon Yellow




S490
Beige




S515
Mosaic Green




S520
Apple Green




S530
Green 48




S540
Green



S550
Olive



S560
Forest Green



S580
Military Green

PU FLEX

DESCRIPTION

Material for laser and plotter cutting applications

SPECIFICATION

Size: 50 cm x 25 m
N.W: 5 kg / roll

TRANSFER CONDITION

The following instructions are given as guideline only.
Temperature: 160°C (320°F)
Pressing Time: 12 seconds

SUITABLE FOR

Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.
Not suitable for treated and dyed garments.

NOTICE

We offer you to test the product against the color migration.
Pressing instruction may change, according to the fabric type.

ÜRÜN TANIMI

Lazer ve plotter kesim uygulamaları için malzeme

ÖZELLİKLER

Ebat: 50 cm x 25 m
Net Ağırlık: 5 kg / roll

BASKI TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlara göredir.
Derece: 160°C (320°F)
Baskı Süresi: 12 saniye

UYGUN KUMAŞLAR


Pamuk, polyester / pamuk karışımı, polyester / akrilik vb tekstiller için uygundur.
Boyanmış ve işlem görmüş kumaşlar için uygun değildir.

UYARI


Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.



Cut the image in reverse
Deseni tersten kesiniz




160°C (320°F)




4 Bar pressure
4 Bar basınç




12 seconds for pressing
12 saniye presleme



WARM Peel
Ilık çekim



45°



After 24H with application
Uygulamadan 24 saat sonra