



GLOW IN THE DARK (180-200 MICRON)

HT500A
Lime Green

GLOW IN THE DARK + REFLECTIVE + FLUO COLOR (300 MICRON)

HT553A
Fluo Yellow



HT554A
Fluo Green



HT558A
Fluo Orange



HT511A
Fluo Pink

GLOW IN THE DARK / GLOW IN THE DARK + REF + FLUO

DESCRIPTION

GLOW IN THE DARK - Laser and plotter cutting
GLOW IN THE DARK + REFLECTIVE + FLUO COLOR - Only for plotter cutting applications

SPECIFICATION

GLOW IN THE DARK
Size: 50 cm x 25 m
N.W: 6,65 kg / roll

GLOW IN THE DARK + REFLECTIVE + FLUO COLOR
Size: 50 cm x 25 m
N.W: 8,25 kg / roll

TRANSFER CONDITION

The following instructions are given as guideline only.
Temperature: 160°C (320°F)
Pressing Time: 12 seconds

SUITABLE FOR

*Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.
Not suitable for treated and dyed garments.*

NOTICE

*We offer you to test the product against the color migration.
Pressing instruction may change, according to the fabric type.*

ÜRÜN TANIMI

GLOW IN THE DARK - Lazer ve plotter kesim
GLOW IN THE DARK + REFLECTIVE + FLUO COLOR - Sadece plotter kesim uygulamaları için malzeme

ÖZELLİKLER

GLOW IN THE DARK
Ebat: 50 cm x 25 m
Net Ağırlık: 6,65 kg / roll

GLOW IN THE DARK + REFLECTIVE + FLUO COLOR
Ebat: 50 cm x 25 m
Net Ağırlık: 8,25 kg / roll

BASKI TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlara göre.
Derece: 160°C (320°F)
Baskı Süresi: 12 saniye

UYGUN KUMAŞLAR


*Pamuk, polyester / pamuk karışımı, polyester / akrilik vb tekstiller için uygundur.
Boyanmış ve işlem görmüş kumaşlar için uygun değildir.*

UYARI


Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.



Cut the image in reverse
Deseni tersten kesiniz




160°C (320°F)




4 Bar pressure
4 Bar basınç



12 seconds for pressing
12 saniye presleme



COOL Peel
Soğuk çekim



45°



After 24H with application
Uygulamadan 24 saat sonra