


HOLOGRAM (100 MICRON)




H-01
Silver




H-02
Gold




H-03
Fuchsia



H-04
Pink




H-05
Red



H-06
R/Blue



H-07
Violet




H-08
Green




H-09
Purple




H-10
Black




H-11
Sky




H-12
Orange



H-13
Aqua



H-14
L/Green



H-15
Brown




H-16
S/Silver



H-17
Rainbow(A)



H-18
Rainbow(B)




CR
Crystal




CRG-G
Crystal


SOLID FOIL (100 MICRON)



N-01
Silver




N-02
Gold




N-03
Fuchsia



N-04
Pink



N-05
Red



N-06
R/Blue



N-07
Violet



N-08
Green




N-09
Sky




N-10
Black




N-11
Clear




N-12
Orange



N-13
Aqua




N-14
L/Green




N-15
Copper



N-16
Mint



N-17
L/Brown



N-18
Grey



N-19
M/Silver



N-20
Rainbow



N-21
White

HOLOGRAM / SOLID FOIL

DESCRIPTION

Material for laser and plotter cutting applications

SPECIFICATION

Size: 50 cm x 100 m
N.W: 14 kg / roll

TRANSFER CONDITION

The following instructions are given as guideline only.
Temperature: 160°C (320°F)
Pressing Time: 12 seconds

SUITABLE FOR

*Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.
Not suitable for treated and dyed garments.*

NOTICE

*We offer you to test the product against the color migration.
Pressing instruction may change, according to the fabric type.*

ÜRÜN TANIMI

Lazer ve plotter kesim uygulamaları için malzeme

ÖZELLİKLER

Ebat: 50 cm x 100 m
Net Ağırlık: 14 kg / roll

BASKI TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlara göredir.
Derece: 160°C (320°F)
Baskı Süresi: 12 saniye

UYGUN KUMAŞLAR


*Pamuk, polyester / pamuk karışımı, polyester / akrilik vb tekstiller için uygundur.
Boyanmış ve işlem görmüş kumaşlar için uygun değildir.*

UYARI


Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.



Cut the image in reverse
Deseni tersten kesiniz




160°C (320°F)




4 Bar pressure
4 Bar basınç




12 seconds for pressing
12 saniye presleme



COOL Peel
Soğuk çekim



45°



After 24H with application
Uygulamadan 24 saat sonra