


GLITTER (300-350 MICRON)



GS-01




GS-02



GS-03



GS-05



GS-06



GS-07



GS-08



GS-09



GS-10



GS-11



GS-12



GS-17



GS-18



GS-19



GS-20



GS-24



GS-25




GS-26




GS-27



GS-32



GS-33



GS-35



GS-41



GS-45



GS-46



GS-63

GLITTER

DESCRIPTION

Material for laser and plotter cutting applications

SPECIFICATION

Size: 50 cm x 50 m
N.W: 11 kg / roll

TRANSFER CONDITION

The following instructions are given as guideline only.
Temperature: 160°C (320°F)
Pressing Time: 12 seconds

SUITABLE FOR

*Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.
Not suitable for treated and dyed garments.*

NOTICE

*We offer you to test the product against the color migration.
Pressing instruction may change, according to the fabric type.*

ÜRÜN TANIMI

Lazer ve plotter kesim uygulamaları için malzeme

ÖZELLİKLER

Ebat: 50 cm x 50 m
Net Ağırlık: 11 kg / roll

BASKI TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlara göredir.
Derece: 160°C (320°F)
Baskı Süresi: 12 saniye

UYGUN KUMAŞLAR


*Pamuk, polyester / pamuk karışımı, polyester / akrilik vb tekstiller için uygundur.
Boyanmış ve işlem görmüş kumaşlar için uygun değildir.*

UYARI


Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.



Cut the image in reverse
Deseni tersten kesiniz




160°C (320°F)




4 Bar pressure
4 Bar basınç




12 seconds for pressing
12 saniye presleme



COOL Peel
Soğuk çekim



45°



After 24H with application
Uygulamadan 24 saat sonra